

TremPro® 640/642

Sprayable or Brushable Polyurethane Coatings

Product Description

TremPro 640 and TremPro 642 are one-part liquid polyurethane coatings for industrial use.

Basic Uses

TremPro 640/642 are used to create a tough, adherent waterproof coating on the inside or outside of containers or similar items where preventing water penetration is important.

TremPro 640/642 are designed primarily for use on concrete and masonry substrates in both vertical and horizontal applications. Both coatings can also be used to seal rivets, bolts, etc.

TremPro 640/642 can also be used for sealing truck bodies, containers, railroad cars, travel trailers, mobile homes, for the assembly of galvanized air conditioning duct work, for narrow joints between wood or metal sections, between masonry and aluminum or stainless steel, and between galvanized metal sections.

Color

Aluminum

Packaging

1 Gallon and 5 Gallon

Surface Preparation

For good adhesion, the joint surface must be sound, clean and dry. Depending on the substrate, the joint surface may require a thorough wire brushing with a steel wool or Scotch Brite pad and/or solvent wipe.

Application

Bulk units of TremPro 640/642 are very easy to apply. The low viscosity of TremPro 640 allows it to be brushed or sprayed with relative ease onto the necessary substrate. TremPro 642 is a higher viscosity semi-solid and can be applied with relative ease by brushing the material on the desired surface.

Maintenance

Damaged coatings can be repaired. Consult Tremco Technical Services or your local Tremco Sales Representative for repair procedures.

Warranty

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace, or refund the purchase of the quantity of Tremco Product proven to be defective and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

TYPICAL PHYSICAL PROPERTIES

Property	Typical Value
Cure Rate	10-12 Hours
Viscosity	TG 640: 5-10,000cps TG 642: 25-30,000 cps
Shore A Hardness	75
Tensile Strength	270-290 psi
Elongation	380-400%
Accelerated Weathering	Excellent
Water Absorption	none



Tremco Commercial Sealants & Waterproofing

3735 Green Road, Beachwood, OH 44122 // Phone: 216.292.5000 // 800.321.7906
220 Wicksteed Avenue, Toronto, ON M4H 1G7 // Phone: 416.421.3300 // 800.363.3213
1451 Jacobson Avenue, Ashland OH 44805 // Phone: 419.289.2050 // 800.321.6357