

### Product Description

An ultra lightweight, extremely tough 14-oz protection mat for waterproofing membranes in both vertical and horizontal applications. It is made of non-biodegradable polyester and can be installed within minutes over a cured membrane to give maximum protection against backfill, poured slabs and other trades.

### Availability

Immediately available from your local Tremco Sales Representative, Tremco Distributor or Tremco Warehouse.

### Coverage Rates

667 ft<sup>2</sup> / roll

### Packaging

40" x 200' (1.0 M x 60.6 M) / roll

Palletized: 12 rolls / pallet

Weight: 65 lb (29.5 kg)

### Installation

This protection mat may be loose laid to the membrane in horizontal applications. It will remain in place by adhering to the waterproofing membrane. In vertical applications, it should be mechanically fastened at the termination line of the waterproofing membrane. Overlap a minimum of 2".

### Warranty

Tremco warrants its Products to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or to refund the purchase price of the quantity of Tremco Product proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

## TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUES
Fabric Weight	ASTM D3776	12 to 14 oz/ly <sup>2</sup>
Thickness	ASTM D1777	100 mils
Grab Tensile	ASTM D4632	300 x 260 lb
Puncture	ASTM D4833	110 lb
Impact Resistance	Drop Ball	Pass
Mullen Burst	ASTM D3786	410 psi
Water Permeability	ASTM D4491	0.56 cm / sec <sup>-1</sup>
Air Permeability	ASTM D4491	2.01 cm / sec <sup>-1</sup>
Planar Flow	ASTM D4491	150 gpm /M <sup>2</sup>
Trap. Tear	ASTM D4533	110 x 100 lb

0316/PROTECTMATDS-BG

### Tremco Commercial Sealants & Waterproofing

3735 Green Rd  
Beachwood OH 44122  
216.292.5000 / 800.321.7906

1451 Jacobson Ave  
Ashland OH 44805  
419.289.2050 / 800.321.6357

220 Wicksteed Ave  
Toronto ON M4H1G7  
416.421.3300 / 800.363.3213

1445 Rue de Coulomb  
Boucherville QC J4B 7L8  
514.521.9555

