

MasterEmaco® P 124

Water-based epoxy-cementitious bonding agent and rebar coating

FORMERLY EMACO® P24

PACKAGING

2.7 GALLON (38.4 LB) KIT:

- Part A: 0.42 gal (1.6 L) epoxy resin
- Part B: 0.42 gal (1.6L) epoxy hardener
- Part C: 31 lbs (14.1 kg) cementitious component

4.8-GALLON (68.0 LB) KIT

- Part A: 0.74 gal (2.8 L) epoxy resin
- Part B: 0.74 gal (2.8 L) epoxy hardener
- Part C: 55 lbs (24.9 kg) cementitious component

YIELD

The coverage is 80 ft²/gal (2.0 m²/L) at a thickness of 20 mils (0.5 mm).

STORAGE

Store and transport in unopened containers in a cool, clean, dry area. Keep from freezing.

SHELF LIFE

1 year when properly stored

VOC CONTENT

0 g/L less water and exempt solvents

DESCRIPTION

MasterEmaco P 124 is a water-based epoxy-cementitious bonding agent. It is also used to coat and protect rebar.

PRODUCT HIGHLIGHTS

- Extended open time
- Integral corrosion inhibitor provides additional protection for reinforcing steel
- High alkalinity; compatible with cementitious materials
- Premeasured units
- Blue color facilitates proper coverage

APPLICATIONS

- Bonding plastic concrete to hardened concrete
- Coating steel rebar to protect against corrosion
- Areas where short open times prevent the use of traditional epoxies

SUBSTRATES

- Concrete
- Steel

HOW TO APPLY

SURFACE PREPARATION

CONCRETE

1. Concrete must be structurally sound and fully cured (28 days).
2. The surface to be repaired must be clean, strong, saturated surface-dry (SSD) and prepared in accordance with ICRI Guideline no. 310.2 to permit proper bond.
3. The clean substrate must be alkaline (pH above 9.5)

REINFORCING STEEL

Remove all oxidation and scale from the exposed reinforcing steel in accordance with ICRI Technical Guideline No. 310.1R.

MIXING

1. Precondition all components to 70 F (21 C). Thoroughly stir each liquid component before mixing.
2. Pour contents of Part A and Part B into a clean mixing bucket and blend the two components for 2 minutes. Slowly add all of Part C. Use a Jiffy paddle and a drill to properly mix the product.

Technical Data

Composition

MasterEmaco P 124 is a water-based epoxy-cementitious bonding agent.


Test Data

PROPERTY	RESULTS	TEST METHOD
Pot life , mixed 150 g, min, at 72° F (22° C)	90	
Working time , min, at 72° F (22° C)	30	
Compressive strength , psi (MPa), 28 days	8,000 (55.2)	ASTM C 109
Flexural strength , psi (MPa), 28 days	1,000 (6.9)	ASTM C 348
Tensile bond strength , 14 days		ACI 503R
Open time , hrs	Psi (MPa)	
2	> 200 (1.4)	
9	> 200 (1.4)	
24	> 200 (1.4)	
Slant shear bond , 14 days		ASTM 882
Open time , hrs	Psi (MPa)	
2	> 3,000 (20.7)	
9	> 2,500 (17.2)	
24	> 2,000 (13.7)	
Splitting tensile , psi (MPa), 28 days	1,000 (6.9)	ASTM C 496

Test results are averages obtained under laboratory conditions. Expect reasonable variations.

Tensile Bond Strength

According to ACI 503R at 28 days,
Topping applied 12 hours after MasterEmaco P 124.



APPLICATION

Apply with a stiff-bristled broom or sprayer. With any method, be sure to work the bonding agent thoroughly into the substrate. Apply at a rate of 20 wet mils (0.5 mm). When applying to rebar, two coats of 10 mils (0.25 mm) will be required. Protect bonding agent from direct sunlight and temperatures above 95° F (35 °C).

CLEAN UP

Clean up with soap and water. Dried material must be removed mechanically.

FOR BEST PERFORMANCE

- Substrate and ambient temperature must be from 40 to 95° F (4 to 35° C).
- When MasterEmaco P 124 is used as a bonding agent for overlays or toppings, obtain best results by topping within 6 hours of application.
- Do not add solvent, water, or any other material to the product.
- Precondition components to approximately 70° F (21° C) for 24 hours before using.
- Protect from direct sunlight, wind, and other conditions that could cause rapid drying of material.
- For professional use only; not for sale to or use by the general public.
- Make certain the most current versions of product data sheet and SDS are being used; visit master-builders-solutions.basf.us to verify the most current version.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and are not for supervising or providing quality control on the jobsite.

HEALTH, SAFETY AND ENVIRONMENTAL

Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.master-builders-solutions.basf.us, e-mailing your request to basfbcsst@basf.com or calling 1(800)433-9517. Use only as directed.

**For medical emergencies only,
call ChemTrec® 1(800)424-9300.**

LIMITED WARRANTY NOTICE

BASF warrants this product to be free from manufacturing defects and to meet the technical properties on the current Technical Data Guide, if used as directed within shelf life. Satisfactory results depend not only on quality products but also upon many factors beyond our control. BASF MAKES NO OTHER WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ITS PRODUCTS. The sole and exclusive remedy of Purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the sole option of BASF. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by Purchaser. BASF WILL NOT BE RESPONSIBLE FOR ANY SPECIAL, INCIDENTAL, CONSEQUENTIAL (INCLUDING LOST PROFITS) OR PUNITIVE DAMAGES OF ANY KIND.

Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. BASF reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

