



PROSOCO®

R-Guard®

AIR & WATER BARRIER



INDOOR ADVANTAGE GOLD BUILDING MATERIALS

AirDam®

PROSOCO R-Guard® AirDam® is a gun-grade waterproofing sealant combining the best of silicone and polyurethane properties. Installed as the interior air sealant, AirDam® creates a long lasting, weather-tight seal that prevents moist outside air from entering, and conditioned indoor air from escaping around window and door assemblies. This ensures wind driven rain and condensed water are diverted to the flashing membrane and water resistive barrier before it can enter the living space.

This single component, Silyl-Terminated-Polymer (STP) is easy to gun and tool in all weather conditions. AirDam® is immediately waterproof and can be applied in unfavorable weather conditions to dry or damp substrates, eliminating many weather-related construction delays and accelerating the “drying in” of new buildings.

AirDam® cures quickly to produce a durable, high performance, high movement elastomeric sealant. Appropriate for exterior or interior use, AirDam® is easily applied with standard caulking tools. AirDam® bonds tenaciously and can be used with all types of window and door frame material – vinyl, wood or metal, including painted metal. As a properly applied interior window sealant, AirDam® can substantially reduce a building’s heating and cooling costs.



SEALANT · WATERPROOFING & RESTORATION INSTITUTE

Issued to: PROSOCO, Inc.
Product: PROSOCO R-GUARD® AirDam®

C719: Pass Ext:+50% Comp:-50%

Substrate: Vinyl, Anodized Aluminum, Wood
[all substrates were unprimed]

Validation Date: 10/19/22 – 10/18/27

No. 22-PR01019 Copyright © 2013

SEALANT VALIDATION
www.swronline.org

ADVANTAGES

- Solvent free. Isocyanate free. Complies with all AIM VOC regulations.
- Silane functional polymer provides superior long term adhesion, crack bridging and weathering characteristics.
- Bonds to most common building materials without priming.
- Produces a durable, weather-tight seal.
- Suitable for exterior or interior use.
- Stops penetration of air and water under normal and extreme weather conditions.
- Single component formulation saves time and requires no mixing.
- Easy to gun and tool in all climates.
- Bonds and cures in wet weather and on damp substrates.
- Compatible with most sealants and waterproofing or air barrier components.
- No shrinkage. No staining. Non-yellowing.
- Breathable – allows damp surfaces to dry.
- Will not support mold growth.
- PROSOCO R-Guard® Joint & Seam Filler, FastFlash® and AirDam® are recommended for improved performance of all R-Guard air- and water-resistive barrier coatings.
- Illustrations depicting the use of PROSOCO R-Guard® products are available at prosoco.com by downloading the R-Guard Installation Guidelines.

Limitations

- Not for use bridging gaps more than 2 inches wide.
- Not for underwater applications.
- Not for applications in direct contact with strong acids or solvents.
- May have slight incompatibility with some asphaltic materials or butyl adhesives. Always test first.

Product Data Sheet

R-Guard AirDam®

REGULATORY COMPLIANCE

VOC Compliance

R-Guard AirDam® is compliant with the US Environmental Protection Agency's AIM VOC regulations. Visit www.prosoco.com/voccompliance to confirm compliance with individual district or state regulations.

SAFETY INFORMATION

Always read full label and SDS for precautionary instructions before use. Use appropriate safety equipment and job-site controls during application and handling.

24-Hour Emergency Information:
INFOTRAC at 800-535-5053

TYPICAL TECHNICAL DATA

FORM	viscous white paste, mild odor
SPECIFIC GRAVITY	1.35–1.50
pH	not applicable
WT/GAL	11.66 lbs
TOTAL SOLIDS	98%
VOC CONTENT	30 g/L maximum
FLASH POINT	>200 ° F (>93° C)
FREEZE POINT	not applicable
SHELF LIFE	1 year in tightly sealed, unopened container

Cured Properties

Hardness, Shore A	30–40
Tensile Strength	150–200 psi
Elongation at Break	>800% (ASTM D 412)
Peel Strength	25 pli

PREPARATION

AirDam® bonds tenaciously. Carefully protect people, vehicles, property, plants, and all other surfaces not intended to receive AirDam®. Immediately clean up incidental contact using mineral spirits or similar solvent.

Surfaces must be structurally sound and free of any surface contaminants, chemical residues, surface coatings or films that may adversely affect adhesion.

Pressure-treated wood or fire-retardant wood and other contaminated surfaces should be cleaned with an Isopropyl Alcohol wipe and allowed to flash-off before application of R-Guard products.

Joint Preparation

For joints less than one-half (½) inch wide, sealant depth should be equal to the width of the joint.

For joints ranging from one-half (½) to one (1) inch wide, sealant depth should be approximately one-half (½) the joint width.

In deep joints, control sealant depth by installing closed cell backer rod. The diameter of soft backer rod should be 25% greater than the joint width. Do not puncture backer rod.

Where joint depth does not permit use of a backer rod, install bond breaker tape to prevent three point bonding.

Surface and Air Temperatures

Substrate and temperature conditions should be 32°F (0°C) and rising and below 110°F (43°C) during application and drying. If air or surface temperatures exceed 95°F (35°C), apply to shaded surfaces and before daytime air and surface temperatures reach their peak.

Hot Weather Installations: when practical install AirDam® to shaded surfaces. When conditions are hot and dry, cool and dampen the surface with a fresh water mist. Allow standing water to dry before installation.

Though AirDam® may be applied to damp surfaces and tolerates rain immediately after application, do not apply to surfaces with standing water or frost. *Contact PROSOCO if conditions are questionable.* As with any coating, application to substrates with high moisture content may lead to blistering of the material.

Equipment

Apply using a professional caulking gun and standard caulking tools. Avoid over tooling.

To tool the product, use a DRY joint knife slightly wider than the gap or joint opening. Do not use soapy water or solvent to help with the tooling process or to slick the surface profile.

Storage & Handling

Store in a cool, dry place. Keep container tightly closed when not in use. Do not open cartridges or sausages until preparation work has been completed. Do not alter or mix with other chemicals. When stored at or below 80°F (27°C),

Product Data Sheet

R-Guard AirDam®

AirDam® has a shelf life of 12 months after the date of manufacture. This shelf life assumes upright storage of factory-sealed containers. Do not double-stack pallets. Keep out of the reach of children. Dispose of in accordance with local, state and national regulations.

APPLICATION

Before use, read “Preparation” and the Safety Data Sheet.

ALWAYS TEST each surface for suitability and desired results before overall application. Use the following application instructions. Let the surface dry thoroughly before inspection and approval.

Dilution & Mixing

Apply as packaged. Do not dilute or alter, or use for applications other than specified. AirDam® is ready to use. No mixing is required.

Coverage Rates

Coverage varies depending on the width and depth of joints. When overlapping onto adjacent surfaces, rough surface irregularities will reduce coverage. Use the table below as a guideline when estimating sealant requirements.

JOINT SIZE (D x W)	Linear Feet Sealed	
	20-oz Sausage	10.3-oz Cartridge
3/16 x 1/4 inches	64	33
3/16 x 1/2 inches	32	16
1/4 x 1/4 inches	48	25
1/4 x 1/2 inches	24	12
3/8 x 3/8 inches	21	11
3/8 x 5/8 inches	13	6.6
1/2 x 1/2 inches	12	6.2
1/2 x 3/4 inches	8	4.1

Application Instructions

1. Using a professional grade caulking gun, install sealant in a continuous bead without gaps or air pockets.
2. Tool sealant immediately to ensure complete wetting of joint bond surface and to produce a smooth, concave joint profile flush with the edges of adjacent surfaces. Where horizontal and vertical surfaces meet, tool sealant to create a slight cove which will not trap moisture or debris. **DO NOT** use water, soapy water or solvent to tool. Avoid over tooling.

Curing and Drying

AirDam® cures at the rate of 1/8 inch of depth per day. Allow for drying time based on temperature and humidity. High humidity decreases curing and drying time. Low temperatures and low relative humidity will extend curing and drying time.

Cleanup

Clean tools and equipment immediately with mineral spirits or similar solvent.

WARRANTY

The information and recommendations made are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application of our products, nor anticipate every variation encountered in masonry surfaces, job conditions and methods used. The purchasers shall make their own tests to determine the suitability of such products for a particular purpose.

PROSOCO, Inc. warrants this product to be free from defects. **Where permitted by law, PROSOCO makes no other warranties with respect to this product, express or implied, including without limitation the implied warranties of merchantability or fitness for particular purpose.** The purchaser shall be responsible to make his own tests to determine the suitability of this product for his particular purpose. PROSOCO's liability shall be limited in all events to supplying sufficient product to re-treat the specific areas to which defective product has been applied. Acceptance and use of this product absolves PROSOCO from any other liability, from whatever source, including liability for incidental, consequential or resultant damages whether due to breach of warranty, negligence or strict liability. This warranty may not be modified or extended by representatives of PROSOCO, its distributors or dealers.

CUSTOMER CARE

Factory personnel are available for product, environment and job-safety assistance with no obligation. Call 800-255-4255 and ask for Customer Care – technical support.

Factory-trained representatives are established in principal cities throughout the continental United States. Call Customer Care at 800-255-4255, or visit our website at prosoco.com, for the name of the PROSOCO representative in your area.

PRODUCT TEST RESULTS

R-Guard AirDam®



ASTM C 920: STANDARD SPECIFICATION FOR ELASTOMERIC JOINT SEALANTS

TEST	METHOD	CRITERIA	RESULTS
Rheological Properties	ASTM C 639	Vertical Slump at 40± 3.6° F must be ≤ 3/16" Vertical Slump at 122± 3.6° F must be ≤ 3/16" Horizontal Slump at 40± 3.6° F, no deformation Horizontal Slump at 122± 3.6° F, no deformation	Pass: 0 Pass: 0 Pass: no deformation Pass: no deformation
Extrusion Rate	ASTM C 1183 Procedure A	Report Specific Gravity Extrusion Rate ≥ 10.0 mL/min	1.5 59 mL/min
Hardness	ASTM C 661	Indentation Hardness <60	Pass: 23
Effects of Heat Aging	ASTM C 1246	Percent Weight Loss ≤7% Visual Examination for presence of cracks or chalking	Pass: 1% Pass: no cracking or chalking
Tack-Free Time	ASTM C 679	< 72 hours	Pass: 1.4 hours
Stain and Color Change	ASTM C 510	No visible stain or color change	Pass
Adhesion and Cohesion Under Cyclic Movement	ASTM C 719	Aggregate loss in bond and cohesion ≤1½ in ²	Pass 0 on vinyl 0 on aluminum 0 on wood
Adhesion-in-Peel	ASTM C 794	Aggregate loss in bond and cohesion ≥5 lbf	Pass 23 lbf on vinyl 20 on aluminum 15 on wood
Effects of Accelerated Weathering	ASTM C 793 ASTM C 1442	Visual inspection for cracking after accelerated weathering and after cold exposure and low temperature bend ≤ Example #2 in ASTM C 793	Pass: no cracking

SEALANT, WATERPROOFING AND RESTORATION INSTITUTE'S PRODUCT VALIDATION PROGRAM

Adhesion and Cohesion Under Cyclic Movement (±50%)	ASTM C 719	Aggregate loss in bond and cohesion ≤1½ in ²	Pass 0 on vinyl 0 on aluminum 0 on wood
--	------------	---	--

All testing was completed by independent, accredited laboratories.

